



RED GRID LIGHT

 **Inkjet Transfer Paper**
 **Light Color Applications**



212-279-0650
paperhoodinfo@gmail.com
38 W. 32nd Street
Room #800, NYC 10001



BEFORE YOU BEGIN

Use product in well-ventilated area. Keep paper out of high humidity and away from moisture. Store in a cool, dry place. Recommended for use on cotton and cotton/poly blends. Inkjet printers only. No laser printers.

1. PRINTING TRANSFER

Preparing Image

- Print design on the paper with the correct orientation. (Mirror/Reverse the image.) This can be done within the printer's property panel.
- Make sure to select the proper media setting from print menu; check your printer manual for additional printing instructions.

Printing Image

- Print the image on the blank side of the transfer paper. (Not text side.)
- Check printer settings; single-sheet feeding is recommended.

Cutting Out Design

For best results, trim the image before applying to garment.

2. APPLYING TRANSFER

1. Heat Press Application

- Prepare heat press and **350°F**.
- Place heat transfer paper with image facing down in desired position on fabric.
- Using above recommended temperature, apply medium pressure or 15-20 seconds.

OR

2. Hand Iron Application

- Iron on smooth hard surface, not an ironing board.
 - Place a pillow case of T-shirt between the hard surface and your garment.
 - Pre-heat iron on its hottest setting. DO NOT STEAM.
 - Place heat transfer paper with image facing down in desired position on fabric.
 - Step press, with firm pressure, slowly along each side of the image. Hold each press for 45 seconds until entire image has been pressed.
- Total ironing time should be 5-6 minutes for 8.5" x 11" size image.**

3. PEEL AND WEAR

Hot peel Peel the transfer immediately after pressing. Caution, transfer will be hot. For softest hand, stretch transfer while still hot.



Before Washing

Leave finished item for at least 24 hours before washing. Wash inside out in cold water. Dry at normal heat settings. Do not use bleach, fabric softener, or harsh detergents. Do not iron directly over transfer.

IMPORTANT: We thoroughly test each of our products on various substrates using different transfer equipment. However, it is impossible to duplicate all variables using all substrates and transfer equipment. Therefore, it is essential that you test the paper prior to production using your equipment, methods, and substrate material. Heat presses vary in accuracy. Conduct tests to determine the best time and temperature to use with your equipment. Please keep in mind that the Seller's and Manufacturer's maximum obligation shall be to replace any paper that has proven defective. Neither the Seller nor the Manufacturer shall be liable for injury, direct or consequential, arising out of the use of, or inability to use the paper.

INK JET OPAGUE

 Inkjet Transfer Paper
 Dark Color Applications



212-279-0650
paperhoodinfo@gmail.com
38 W. 32nd Street
Room #800, NYC 10001



BEFORE YOU BEGIN

For use in Inkjet Printers only. Keep product out of humid conditions and away from moisture. Store in a cool, dry place.

1. PRINTING TRANSFER

Preparing Image

- Make sure to select the proper media setting from print menu; check your printer manual for additional printing instructions.

Printing Image

- Print design on the paper with the correct orientation. (DO NOT Mirror/Reverse the image.)
- Print the image on the blank side of the transfer paper. (Not text side.)
- Check printer settings; single-sheet feeding is recommended.

Cutting Out Design

- DO NOT leave a margin around the edge of the image. (Cut along image edge.) Leaving a margin around the image will result in a border along the image.
- **Peel off grid backing paper before pressing!**
- This is done by gently peeling the backing apart from the polymer containing image.

3. PEEL AND WEAR

Allow fabric to cool completely before lifting.

2. APPLYING TRANSFER

A. Heat Press Application

- Prepare heat press and **350°F**.
- Place heat transfer paper with image facing upwards in desired position on fabric.
- Cover image with silicone paper.
- Using above recommended temperature, apply medium pressure or **20 seconds**.

OR

B. Hand Iron

- Pre-heat iron to hottest NON-STEAM setting.
- Iron on smooth hard surface, not on ironing board.
- Place pillowcase over hard surface.
- Adjust iron at highest setting. DON'T STEAM.
- Place heat transfer paper with image facing upward in desired position on fabric.
- Cover image with silicone paper.
- Step press, with firm pressure, slowly along each side of the image. Hold each press for **45 seconds** until entire image has been pressed. Total ironing time should be **5-6 minutes** for 8.5" x 11" size image.

* Before Washing

Leave finished item for at least 24 hours before washing. Wash inside out in cold water. Dry at normal heat settings. Do not use bleach, fabric softener, or harsh detergents. Do not iron directly over transfer.

IMPORTANT: We thoroughly test each of our products on various substrates using different transfer equipment. However, it is impossible to duplicate all variables using all substrates and transfer equipment. Therefore, it is essential that you test the paper prior to production using your equipment, methods, and substrate material. Heat presses vary in accuracy. Conduct tests to determine the best time and temperature to use with your equipment. Please keep in mind that the Seller's and Manufacturer's maximum obligation shall be to replace any paper that has proven defective. Neither the Seller nor the Manufacturer shall be liable for injury, direct or consequential, arising out of the use of, or inability to use the paper.